

A Material Difference

# Mediprene® 500M

TPE for Medical Applications - Transparent Series



# CONTENTS

Introduction →

Key Properties →

Regulatory Compliance →

Typical Applications →

Coloured + Transparent Materials →

Grade Table →

Processing →

# Introduction

The Mediprene 500M range of TPEs for medical applications includes several transparent grades. These compounds were developed in response to an increasing interest in transparent compounds from the medical market.

Mediprene TPE materials are PVC, silicone and latex free, making them allergen free and a viable alternative to PVC based compounds. They offer hardnesses from 30 to 90 Shore A, allowing a wide degree of design freedom.

The right TPE formulation is the key to a safe and successful medical product. When a standard formulation does not meet the needs of a unique application, we will apply our expertise in formulating a custom solution. In this guide we show typical properties for our most common grades, these tables do not list all available properties and materials.

Please use this guide as an introduction to the Mediprene 500M transparent series and [contact us](#) to discuss your specific requirements.

# Key Properties

- Good transparency
- PVC, silicone and latex free
- Soft-touch appeal
- 30 to 90 Shore A
- Coloured, transparent grades
- Production site accredited to ISO 13485
- Sterilizable with gamma, ethylene oxide (EtO) and steam
- Flexibility over a broad temperature range
- Excellent sealing and adhesion

# Regulatory Compliance

All Mediprene Transparent TPE Series compounds fulfil a strict raw material selection policy. The raw materials are food contact compliant (FDA 21CFR and Commission Regulation (EU) No 10/2011) and have a proven level of biocompatibility:

- The styrenic block copolymer has passed USP Class VI
- The paraffinic oil is a medicinal white oil, complying with the European Pharmacopoeia for liquid paraffin and USP for mineral oils
- The polypropylene has passed the USP Class VI tests and meets the requirements in the EP Monograph 3.1.3 Polyolefins

Note: Mediprene grades are not to be used in any devices or materials intended for implantation in the human body.

[Further Information on Raw Material Policy + Change Control >](#)



# Application Examples

The ability to clearly see through a product to monitor the patient is an important feature for many medical applications such as face masks.

Mediprene Transparent TPEs can also be used in tubing and dental applications.



# Coloured + Transparent Materials

In medical devices and pharmaceutical packaging colour is also often used functionally for product identification; to differentiate products with different uses or sizes. The vibrant colours achievable with coloured Mediprene TPE compounds allow brand owners to add value to their products and create visual appeal.

A blue or green colour is often used in medical transparent or translucent products to disguise the yellowing phenomena that can be caused by for example gamma sterilization.

The coloured transparent compounds are made from medical grade raw materials only. The colour masterbatch supplier has been selected with care, ensuring that not only the colorants and carriers are compliant with USP Class VI or corresponding parts of ISO 10993 but also that the masterbatches are manufactured under rigorous controls with regard to traceability, consistency and change control, thereby fitting the Mediprene concept at our ISO 13485 accredited facilities.

# Typical Grades

Grade	Hardness <sup>1</sup> ASTM D2240 (4mm) Shore A	Colour	Density ASTM D792 g/cm <sup>3</sup>	Tensile Strength ASTM D638 MPa	Stress at 100% Strain ASTM D638 MPa	Stress at 300% Strain ASTM D638 MPa	Elongation at Break ASTM D638 %	Tear Strength ASTM D624 N/mm	MFR ASTM D1238 g/10 mm
Mediprene 500302M	30	Transparent	0.89	6	0.6	1.2	600	20	25
Mediprene 500352M	35	Transparent	0.89	6	0.8	1.4	700	22	23
Mediprene 500402M	40	Transparent	0.89	6	0.9	1.8	650	25	15
Mediprene 500422M	42	Transparent	0.89	7	0.7	1.5	650	40	14
Mediprene 500452M	45	Transparent	0.89	6	1.1	2.2	550	26	20
Mediprene 500502M	50	Transparent	0.89	6	1.4	2.5	650	28	12
Mediprene 500552M	55	Transparent	0.89	7	1.4	2.8	600	29	12
Mediprene 500602M	60	Transparent	0.89	7	2.0	3.4	600	35	10
Mediprene 500652M	65	Transparent	0.89	7	2.5	3.8	600	36	8
Mediprene 500702M	70	Transparent	0.89	8	3.0	4.8	600	42	5
Mediprene 500752M	75	Transparent	0.89	9	3.3	4.8	500	43	5
Mediprene 500802M	80	Transparent	0.89	10	4.1	5.9	550	48	4
Mediprene 500852M	85	Transparent	0.89	11	5.0	6.5	500	58	5
Mediprene 500902M	90	Transparent	0.89	15	8.0	9.0	600	75	2



# Processing

Mediprene 500M transparent series TPEs can be processed using standard thermoplastic processing methods, including injection moulding and extrusion.

## Processing Temperatures

Extrusion 140 to 180°C

Injection Moulding 150 to 210°C

Mould 20 to 40°C

Service Temperature Range -50 to +100°C (unstressed material)

Adhesion to PP Excellent

Presentation Free flowing pellets that can be processed without predrying, when stored under normal conditions

[Further TPE Processing + Problem Solving Guides >](#)

# More Mediprene TPE Ranges

Click for more information

**Mediprene® 500M**  
Standard Series




**Mediprene® 500M**  
Plunger Seal Series



**Mediprene® A**

2K

**Mediprene® BM**




**Mediprene®**



**Mediprene® OF**

OIL



**Mediprene®**  
Solvent Bondable



# ABOUT US



[info@hexpolTPE.com](mailto:info@hexpolTPE.com) | [www.hexpolTPE.com](http://www.hexpolTPE.com)

**80,000+**  
T/P.A. CAPACITY

Across our Sweden, UK, German, China & North America operations. [Our companies](#)

**50+**  
YEARS HISTORY

We've a proud history in flexible polymer compounding & were among the **1st to produce TPEs** in Europe. [About us](#)

**34,795+**  
FORMULATIONS

A comprehensive portfolio in TPE, TPS, TPO, TPU, TPV, soft PVC & Biobased technologies. Learn more about [Our products](#)

We provide written and illustrated advice in good faith. This should only be regarded as being advisory and does not absolve customers from doing their own full-scale tests to determine the suitability of the material for the intended applications. You assume all risk and liability arising from your use of the information and/or use or handling of any product. HEXPOL TPE makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Figures are indicative and can vary depending on the specific grade selected and the production site. We retain the right to make changes without prior notice. HEXPOL and Dryflex are trademarks of HEXPOL Group, registered or used in many jurisdictions worldwide.